



BLACK SM

A DEEP, TRUE BLACK COLORATION WITH A MODERATELY TEXTURED SURFACE. PAIRS WELL WITH ALL SOLIDS AND WOODGRAINS.

SSI'S 3DL SOLID FINISH HAS A LIGHT TEXTURE AND A GLOSS LEVEL OF AROUND 12-15. THIS SURFACE IS SUITABLE FOR BOTH VERTICAL AND HORIZONTAL APPLICATIONS. IT IS EASY TO CLEAN, DOESN'T CHIP, IS HIGHLY DURABLE AND HAS LONG TERM UV COLOR STABILITY.

[COMPLEMENTARY MATERIALS
CLICK HERE](#)

PENTADecOR® 2D LAMINATE
COLOR CODE: 95/2500





BLACK SM

PENTADECOR® 2D LAMINATE

STOCK RANGE ✓

COLOR CODE: 95/2606 EMBOSSING: A13 ML TOPCOAT: SENDURA

PERFORMANCE SUMMARY

- BLEACH SOLUTION CLEANABLE
- EXCELLENT SOIL & STAIN RESISTANCE
- NATURAL FLUID BARRIER
- EXCELLENT ABRASION & IMPACT RESISTANCE
- EXCELLENT COLOR STABILITY

ENVIRONMENTAL

- NO ADDED FLAME RETARDANTS
- NO ADDED ANTIMICROBIALS
- DOES NOT CONTAIN FORMALDEHYDE
- FORMULATED WITHOUT PHTHALATES

CLEANING AND MAINTENANCE

- WATER AND MILD LIQUID SOAP CLEANABLE

ITEM SPECIFICATIONS

MOQ : NONE

SURFACE TEXTURE/EMBOSSING : SMOOTH SURFACE

SURFACE GLOSS : LEVEL 4

SURFACE FINISH LACQUER : SCRATCH, STAIN, FINGERPRINT RESISTANT SENDURA TC

GAUGE : .008" (200MY) WIDTH : 49.2" (1250MM)

ROLL SIZE : 500 LM/ROLL

DESIGN REPEAT (RAPPORT) : SOLID COLOR ∞

SUITABLE FOR : FLAT LAMINATION – PROFILE WRAPPING – MITER FOLDING

PERFORMANCE CHARACTERISTICS

TENSILE STRENGTH (MD) : N/MM² – >40

LIGHT FASTNESS : WBS – 6–7

CHEMICAL RESISTANCE : CLASS – 1B

SCRATCH RESISTANCE (ERICHSSEN) : 4E

SCRATCH RESISTANCE MARTINDALE A : 25

RESISTANCE TO DRY HEAT : 7C (100 C)

RESISTANCE TO WET HEAT : 8B (70 C)

FLUID BARRIER : INHERENT FLUID BARRIER (NATURALLY HYDROPHOBIC)

MEDICAL REAGENTS : COMPATIBLE WITH COMMON CLEANERS, REAGENTS AND DISINFECTANTS USED IN N.A.

ASTM E84 : CLASS A

REDUCED ENVIRONMENTAL IMPACT: MANUFACTURED WITHOUT PLASTICIZERS, PHTHALATES, OR HEAVY METALS

COMPLEMENTARY MATERIALS
CLICK HERE

Test results may vary by color and design

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be understood as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed.